

# PRODUCT DATA SHEET

## RocCrete-Combo



Two Part acrylic modified highly flexible Cementitious Waterproof Coating

### PRODUCT DESCRIPTION

**RocCrete-Combo** is a liquid applied two component highly flexible acrylic modified cementitious coating system which requires only simple on-site mixing to provide excellent adhesion, flexibility crack bridging ability and durability. Hard wearing, waterproof membrane for roof and foundation protection. In exposed areas it is highly recommended an over coat of Rocshield or RocShield HR RocCrete F20 is a blend of specially selected cements, precisely graded silica, dolomite fillers and chemical admixtures with a liquid component of pure acrylic copolymer and wetting agents.

### ADVANTAGES

- ▶ Waterproof roof coating, Foundation protection.
- ▶ Concrete marine structures
- ▶ Impervious lining for water retaining structures.
- ▶ Backing to marble, preventing staining.
- ▶ Fixing tiles in water tanks.
- ▶ Protection of concrete from sea water ingress.
- ▶ Coating to prevent chloride ion ingress & Carbonation attack
- ▶ Re-profiling concrete surfaces, sealing tie bar holes, general concrete repair

### SPECIFICATION TYPE

Excellent elongation and flexibility Increased frost and salt resistance  
1 mm coating provides anti-carbonation cover to over 80 cm of concrete  
Excellent adhesion, flexible, seamless.  
Provides protection during curing, can be applied to concrete 24 hours old.  
Carbon dioxide diffusivity 360 m (accepted criteria  $R > 50m$ ).  
Waterproof up to 7 bars of pressure. Weather resistant, allows surface to breath. Protects against carbonation and Chloride attack.

### COVERAGE

1.4 kg/m<sup>2</sup> @ 1 mm thickness. 2 coats required.

### TYPICAL PROPERTIES

<b>Color</b>	Off White
<b>Mixed Density ASTM D 1475</b>	1.40 +/-0.05 @ 25°C.
<b>Pot life, [min]</b>	45
<b>Tensile [N/mm<sup>2</sup>] ASTM D 412</b>	3.5
<b>Elongation, [%] ASTM D 412</b>	>250
<b>Crack bridging ability [mm]</b>	>1
<b>Abrasion resistance, [gms] ASTM D 4060</b>	<50
<b>Toxicity BS 6920</b>	Non-toxic
<b>Hydrostatic pressure @5 bar [50m] BS 12390</b>	No leakage Part 8]
<b>Chemical resistance ASTM D 543</b>	pH 2.5-11.5
<b>Adhesion to concrete, [N/mm<sup>2</sup>] ASTM D 4541</b>	>0.5
<b>Application temperature, [°C]</b>	5 to 45
<b>Application temperature, [°C]</b>	5 to 45

## DIRECTIONS FOR USE

**Surface Preparation:** Ensure that surfaces to be treated are free of dust, dirt, grease, oil and other foreign matter. Cut back spilled concrete until sound and make good with a repair mortar such as Roc-Build HF or HL. If repairs have been carried out cure with water or RocCure CL. On old concrete remove all traces of conventional curing compounds and surface sealers prior to application

**Mixing:** RocCrete-Combo is supplied as a powder (part A) and liquid (part B). Using a clean container, slowly add the powder to the liquid component and mix with a slow speed drill fitted with a suitable mixing paddle. RocCrete-Combo should be used directly after mixing. Re-mix occasionally during application; do not re-temper with water.

Mixing full units is recommended, however where required part units maybe mixed providing close attention is paid to mixing ratios. Part units may be required for filling surface imperfections prior to coating the concrete.

**Application:** Thoroughly dampen down the concrete surface with clean water prior to application. Ideal conditions are saturated surface dry (SSD). Do not apply to dry concrete. Whilst damp, apply RocCrete-Combo with a bristle brush or roller at the rate of 1.8 kg/m<sup>2</sup>. This is achievable in one coat on horizontal surfaces although two coats will ensure even coverage and remove pin holing. On vertical or overhead surfaces 2 or 3 coats may be required. Where more than 1 coat is required, the previous coat should be allowed to dry prior to subsequent applications.

Spray application may be suitable for larger areas; airless spray should be used with 3-4 mm nozzle sizes at 6-8 bar pressure. Trials should be conducted to finalize the best method for the application. Ensure continuous supply of mixed product when adopting this surface dry (SSD). Do not apply to dry concrete. Whilst damp, apply RocCrete-Combo with a bristle brush or roller at the rate of 1.8 kg/m<sup>2</sup>. This is achievable in one coat on horizontal surfaces although two coats will ensure even coverage and remove pin holing. On vertical or overhead surfaces 2 or 3 coats may be required. Where more than 1 coat is required, the previous coat should be allowed to dry prior to subsequent applications.

Spray application may be suitable for larger areas; airless spray should be used with 3- 4 mm nozzle sizes at 6-8 bar pressure. Trials should be conducted to finalize the best method for the application. Ensure continuous supply of mixed product when adopting this Excellent method. Equipment should be thoroughly cleaned immediately after use with water. Hardened coating may only be removed mechanically.

As RocCrete-Combo is moisture tolerant it can be applied onto concrete that is only 24 hours old thereby giving immediate protection and curing.

Where heavy depressions, cracks or blowholes are present, reduce the amount of gauging liquid in the mix to the desired consistency and carry out re-profiling. When used in tanking applications allow the coating to cure fully for 72 hours prior to water testing.

## PACKAGING & STORAGE

20 kg units (10 kg powder/ 10 kg liquid). Complete un-opened units should be stored in shaded ware- houses away from heat, humidity or moisture. Shelflife 12 months.

## HEALTH & SAFETY

Care should be taken during use and storage to avoid contact with eyes, mouth, skin and foodstuffs. Treat splashes to eyes and skin immediately. If ingested, seek immediate medical attention.

## PRODUCT RANGE

**RocSeal CP20-** surface applied capillary water-proofing and plugging system.

**RocShield-** high performance, liquid applied acrylic roofing system.

**RocCoat SB prime-** solvated coating & primer.

**RocCoat RBE-** rubberized bitumen emulsion.

**RocCoat WB primer-** bitumen emulsion coat.

Please read all information in the general guidelines, product data sheets, guide specifications and material safety data sheets (MSDS) before applying material. Published technical data and instructions are subject to change without notice. Contact your local or Products representative or visit our website for current technical data and instructions.

### Disclaimer

All guidelines, recommendations, statements, and technical data contained herein are based on information and tests we believe to be reliable and correct, but accuracy and completeness of said tests are not guaranteed and are not to be construed as a warranty, either expressed or implied. It is the users responsibility to satisfy himself, by his own information and test, to determine suitability of the product for his own intended use, application and job situation and user assumes all risk and liability resulting from his use of the product. We do not suggest or guarantee that any hazard listed here in are the only ones which may exist. Neither seller nor manufacturer shall be liable to the buyer or any thirdperson for any injury, loss or damage directly or indirectly resulting from use of, or inability to use, the product. Recommendations or statements, whether in writing or oral, other than those contained herein shall not be binding upon the manufacturer, unless in writing and signed by a corporate officer of the manufacturer. Technical and application information is provided for the purpose of establishing a general profile of the material and proper application procedures. Test performance results were obtained in a controlled environment and GET makes no claim that these tests or any other tests, accurately represent all environments.